		ARS Doold BOTTON			
FORM PTO-1390 U.S., DEPAI P16370.P03	RTMENT OF COMMERCE PATENT AND TRADEMARK	OFFICE RECIDENCE FEB 1998			
TRANSMITTAL LETTER TO THE UNITED STATES		P16370 09 /011634			
DESIGNATED/ELECTED OFFICE CONCERNING A FILING UNDER 3		U.S. APPLICATION NO. (If known, see 37 CFR 1.5)			
INTERNATIONAL APPLICATION NO.	INTERNATIONAL FILING DATE	PRIORITY DATE CLAIMED			
PCT/NL96/00323	16 August 1996	17 August 1995			
TITLE OF INVENTION					
INTERMEDIATE TRANSFER BLANKET AND M	ETHOD OF PRODUCING THE SAME				
APPLICANT(S) FOR DO/EO/US					
Marc ARONHIME, Frida AVADIC, David	IDAN, Nava KLEIN, Yael KOWAL, Benny LA	NDA, Amiran LAVON, Yehuda NIV, and Carlos TEPER			
Applicant herewith submits to the L	nited States Designated/Elected Office	(DO/EO/US) the following items and other information:			
1. <u>X</u> This is a FIRST submission o	f items concerning a filing under 35 U	.S.C. 371.			
2 This is a SECOND or SUBSEQUE	NT submission of items concerning a fi	ling under 35 U.S.C. 371.			
3. X This express request to begi examination until the expira	n national examination procedures (35) tion of the applicable time limit set	U.S.C. 371(f)) at any time rather than delay in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).			
4. <u>X</u> A proper Demand for Internat date.	ional Preliminary Examination was made	by the 19th month from the earliest claimed priority			
 a. X is transmitted herewit b. X has been transmitted b 	Application as filed (35 U.S.C. 371(c)) h (required only if not transmitted by y the International Bureau. e application was filed in the United S	the International Bureau).			
A Translation of the Interna	tional Application into English (35 U.s	S.C. 371 (c)(2)).			
bhave been transmitted chave not been made; ho d. X have not been made and	wever, the time limit for making such a	the International Bureau).			
A translation of the amendmen	nts to the claims under PCT Article 19	(35 U.S.C. 371(c)(3))			
An oath or declaration of the	e inventor(s) (35 U.S.C. 371(c)(4)).				
	to the International Preliminary Exami	nation Report under PCT Article 36 (35 U.S.C. 371(c)(5)).			
	document(s) or information included:				
An Information Disclosure Sta	atement under 37 CFR 1.97 and 1.98.				
2 An assignment document for re	ecording. A separate cover sheet in co	ompliance with 37 CFR 3.28 and 3.31 is included.			
34 <u>X</u> A FIRST preliminary amendment	:. ninary amendment.				
4 A substitute specification.					
5 A change of power of attorney	and/or address letter.				
PCT/IPEA/416. PCT/IPEA/409 International Pr Letter dated November 11, 199 PCT/IPEA/408 Written Opinion. PCT/IB/308.	International Application as filed). eliminary Examination Report(with eigh 7 in reference to comments to first wr	t pages of amended sheets). itten opinion of August 11.			
PCT/IB/304. PCT/RO/105.	774 AND 77 0 5 - 1 10-	1 1			
Cover Letter under 35 U.S.C. Claim of Priority. PCT/ISA/210 International Sea					

<u>f</u> :

U.S. APPLICATION NO. (If known, see 3,7 CFR 1.5) INTERNATIONAL APPLICATION NO. PCT/NL96/00323			ATTORNEY'S DOCKET NUMBER P16370		
17X_ The following fees are submitted:				CALCULATIONS	PTO USE ONLY
Basic Nation	al Fee (37 CFR 1.492(a)(1)-(5)):			
Search report	has been prepared by the EPO	or JPO\$930.00			
International	preliminary examination fee	paid to USPTO (37 CFR 1.482)\$720.00			
No internation international	al preliminary examination f search fee paid to USPTO (37	ee paid to USPTO (37 CFR 1.482) but CFR 1.445(a)(2))\$790.00			
Neither international	ational preliminary examinat search fee (37 CFR 1.445(a)(ion fee (37 CFR 1.482) nor 2)) paid to USPTO\$1,070.00			
International p	oreliminary examination fee ped provisions of PCT Article	paid to USPTO (37 CFR 1.482) and all 33(2)-(4)\$98.00			
		ENTER APPROPRIATE BASIC FEE	AMOUNT =	\$	930.00
Surcharge of \$130.00 months from the ear	O for furnishing the oath or liest claimed priority date	declaration later than 20 30 (37 CFR 1.492(e)).		\$	0.00
Claims	Number Filed	Number Extra	RATE	\$	0.00
Total Claims	65 - 20 =	45	X \$22.00	\$	990.00
Independent Claims	10 - 3 =	7	X \$82.00	\$	574.00
Multiple dependent o	claim(s) (if applicable)		+ \$270.00	\$	0.00
H 100 H 100 H 100		TOTAL OF ABOVE CALCUL	ATIONS =	\$	2,494.00
must also be filed.	filing by small entity, if (Note 37 CFR 1.9, 1.27, 1.2	applicable. Verified Small Entity Statem 8)	ient	\$	- 0.00
		SU	BTOTAL =		2,494.00
Processing fee of \$1 months from the earl	30.00 for furnishing the Engliest claimed priority date (lish translation later than 20 30 37 CFR 1.492(f)).	+		0.00
	ee in the amount of \$		+		0.00
# 574		TOTAL NATION	AL FEE =		2,494.00
Fee for recording th accompanied by an ap	e enclosed assignment (37 CF propriate cover sheet (37 CF	R 1.21(h)). The assignment must be R 3.28, 3.31). \$40.00 per property	+		0.00
		TOTAL FEES EN	CLOSED =		2,494.00
and the second s				Amount to be refunded	\$ 0.00
				charged	\$ 0.00
a. <u>X</u> A check in the	amount of \$2,494.00 to cove	r the above fees is enclosed.			
b Please charge A duplicate co	my Deposit Account No. py of this sheet is enclosed	in the amount of \$ to cove -	r the abov	e fees.	
c. <u>X</u> The Commission Deposit Accoun	er is hereby authorized to c t No. <u>19-0089</u> . A duplicate	harge any additional fees which may be re copy of this sheet is enclosed.	quired, or	credit any overpa	yment to
NOTE: Where an appromust be filed and gr	opriate time limit under 37 anted to restore the applica	CFR 1.494 or 1.495 has not been met, a pe tion to pending status.	tition to	revive (37 CFR 1.1	37(a) or (b))
SEND ALL CORRECTORDE	NCE TO:			Mars 1	
SEND ALL CORRESPONDE: Arnold Turk	NCE 10:		Sig	MATURE .	
GREENBLUM & BERNSTEII 1941 Roland Clarke P					
Reston, VA 20191 (703) 716-1191	· · · · · · · · · · · · · · · · · · ·		<u>Arn</u> NAM	old Turk E	
			وت وڻ	201	
			<u>33,</u> REG	1STRATION NUMBER	

	· · · · · · · · · · · · · · · · · · ·				
FORM PTO-1390 U.S. DEPARTMENT	OF COMMERCE PATENT AND TRADEMÄR	OFFICE OF ATTORNEY S BOOK NUMBER R 03 1998			
TRANSMITTAL LETTER TO THE UNITED DESIGNATED/ELECTED OFFICE (DO/EC		U.S APPLICATION NO. (If known, see 37 CFR 1.5)			
CONCERNING A FILING UNDER 35 U.S.		09/011,634			
INTERNATIONAL APPLICATION NO.	INTERNATIONAL FILING DATE	PRIORITY DATE CLAIMED			
PCT/NL96/00323	16 August 1996	17 August 1995			
TITLE OF INVENTION	<u> </u>				
INTERMEDIATE TRANSFER BLANKET AND METHOD	OF PRODUCING THE SAME				
APPLICANT(S) FOR DO/EO/US Marc ARONHIME, Frida AVADIC, David IDAN	J, Nava KLEIN, Yael KOWAL, Benny (LANDA, Amiran LAVON, Yehuda NIV, and Carlos TEPER			
Applicant herewith submits to the United	d States Designated/Elected Office	e (DO/EO/US) the following items and other information:			
1 This is a FIRST submission of ite	ems concerning a filing under 35 (U.S.C. 371.			
2. \underline{X} This is a SECOND or SUBSEQUENT su	ubmission of items concerning a f	iling under 35 U.S.C. 371.			
 This express request to begin nate examination until the expiration 	tional examination procedures (35 of the applicable time limit set	U.S.C. 371(f)) at any time rather than delay in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).			
4 A proper Demand for International date.	l Preliminary Examination was mad	e by the 19th month from the earliest claimed priority			
A copy of the International Appl ais transmitted herewith (re bhas been transmitted by the cis not required, as the app	equired only if not transmitted b e International Bureau.)(2)). y the International Bureau). States Receiving Office (RO/US).			
6. $\frac{\int_{\frac{1}{2\pi i}}^{\frac{1}{2\pi i}}}{\frac{1}{2\pi i}}$ A Translation of the Internation	al Application into English (35 U	.s.c. 371 (c)(2)).			
Amendments to the claims of the aare transmitted herewith () bhave been transmitted by the chave not been made; however dhave not been made and will	required only if not transmitted ne International Bureau. r, the time limit for making such	by the International Bureau).			
8. = A translation of the amendments	to the claims under PCT Article 1	9 (35 U.S.C. 371(c)(3))			
9. X An oath or declaration of the in	ventor(s) (35 U.S.C. 371(c)(4)).				
"EXECUTED" 10 A translation of the annexes to	the International Preliminary Exa	mination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).			
Items 11. to 16. below concern other do	cument(s) or information included	:			
An Information Disclosure Statem	ent under 37 CFR 1.97 and 1.98.				
12 An assignment document for record	ding. A separate cover sheet in	compliance with 37 CFR 3.28 and 3.31 is included.			
13 A FIRST preliminary amendment A SECOND or SUBSEQUENT prelimina	ry amendment.				
14 A substitute specification.					
15 A change of power of attorney and	d/or address letter.				
16. <u>X</u> Other items or information: Cover Letter (in triplicate)					
04/17/1998 PVDLPE 00000073 09011634					
01 FC:154 130.0	0 OP				
AT : maya.					

U.S. APPLICATION NO. (If known, see 37 CFR 1.5) INTERNATIONAL APPLICATION NO. PCT/NL96/00323			ATTORNEY'S DOCKET NUMBER P16370		
17 The following fees are submitted:				CALCULATIONS	PTO USE ONLY
Basic Nation	al Fee (37 CFR 1.492(a)(1)-(5)):			
Search report	has been prepared by the EPO	or JP0\$930.00			
International	preliminary examination fee p	aid to USPTO (37 CFR 1.482)\$720.00			
No internation	al preliminary examination fe search fee paid to USPIO (37	e paid to USPTO (37 CFR 1.482) but CFR 1.445(a)(2))\$790.00			
Neither international	ational preliminary examinatio search fee (37 CFR 1.445(a)(2)	on fee (37 CFR 1.482) nor)) paid to USPTO\$1,070.00			
International p	oreliminary examination fee pa ed provisions of PCT Article :	aid to USPTO (37 CFR 1.482) and all 33(2)-(4)\$98.00			T
		ENTER APPROPRIATE BASIC FEE A	AMOUNT =	\$	0.00
Surcharge of \$130.00 months from the ear	O for furnishing the oath or oliest claimed priority date (3	declaration later than 20 30 37 CFR 1.492(e)).		\$	130.00
Claims	Number Filed	Number Extra	RATE	\$	0.00
Total Claims	- 20 =	х	\$22.00	\$	0.00
Independent Claims	- 3 =	x	\$82.00	\$	0.00
Multiple dependent o	claim(s) (if applicable)	+	\$270.00	\$	0.00
		TOTAL OF ABOVE CALCULA	TIONS =	\$	130.00
must also be filed.	filing by small entity, if a (Note 37 CFR 1.9, 1.27, 1.28	pplicable. Verified Small Entity Stateme	nt	\$	- 0.00
inesi inesi		SUB	TOTAL =		130.00
Processing fee of \$1 months from the earl	30.00 for furnishing the Engliest claimed priority date (3	ish translation later than 20 30 7 CFR 1.492(f)).	+		0.00
7.1	ee in the amount of \$		+		0.00
3		TOTAL NATIONA	L FEE =		130.00
accompanied by an ap	e enclosed assignment (37 CFR propriate cover sheet (37 CFR	1.21(h)). The assignment must be 3.28, 3.31). \$40.00 per property	+		0.00
The state of the s		TOTAL FEES ENC	LOSED =		130.00
# 1				Amount to be refunded	\$ 0.00
				charged	\$ 0.00
a. <u>X</u> A check in the	amount of \$130.00 to cover to	he above fees is enclosed.			
	my Deposit Account No. py of this sheet is enclosed.	in the amount of \$ to cover	the abov	e fees.	
c. <u>X</u> The Commission Deposit Accoun	er is hereby authorized to chart No. <u>19-0089</u> . A duplicate ca	arge any additional fees which may be requ opy of this sheet is enclosed.	uired, or	credit any overpa	yment to
NOTE: Where an appromust be filed and gra	opriate time limit under 37 CH anted to restore the applicat	FR 1.494 or 1.495 has not been met, a petion to pending status.	ition to	evive (37 CFR 1.1	37(a) or (b))
SEND ALL CORRESPONDE	NCE TO:		<u> </u>		ZC
Arnold Turk GREENBLUM & BERNSTEI)	N. P. L.C.		816	PATURE / / /	
1941 Roland Clarke Pi Reston, VA 20191				old Turk	
(703) 716-1191			NAMI		
			<u>33,0</u> REG	STRATION NUMBER	
					[

Rec'd PCT/PTO 1 9 FEB 1998

09/011634

P16370.A01

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant

: ARONHIME et al.

Appl. No

: Not Yet Assigned

(National Stage of PCT/NL96/00323)

Filed

: August 16, 1996

For

: INTERMEDIATE TRANSFER BLANKET AND METHOD

OF PRODUCING THE SAME

PRELIMINARY AMENDMENT AND COVER LETTER SUBMITTING AMENDED PAGES OF APPLICATION

Commissioner of Patents and Trademarks Washington, D.C. 20231

Sir:

Enclosed please find a copy of the International Preliminary Examination Report - Form PCT/IPEA/409 (hereinafter "Report") which was drawn on the originally filed description and drawings, and claims 1-65 as filed on November 11, 1997, and includes as an Annex amended sheets 30-37 including claims 1-65.

Based upon the submission of amended sheets of claims, Applicants respectfully request examination on the merits of the application containing amended pages 30-37 of claims, including claims 1-65, in place of the originally filed international claims.

Additionally, prior to the examination of the above-identified application including replacement claims 1-65, amendment of the claims to remove multiple dependent claims is respectfully requested.

IN THE CLAIMS

Please amend replacement claims 3, 4, 7-13, 15, 17-20, 24-28, 35-45, 51, 55-57, as follows:

Claim 3, line 1, delete "or claim 2".

Claim 4, line 1, change "any of the preceding claims" to --- claim 1---.

Claim 7, line 1, delete "or claim 6".

Claim 8, line 1, delete "or claim 6".

Claim 9, line 1, change "any of claims 4-7" to ---claim 4---.

Claim 10, line 1, change "any of claims 4-8" to ---claim 4---.

Claim 11, line 1, change "any of the preceding claims" to ---claim 1---.

Claim 12, line 1, change "any of claims 1-10" to ---claim 1---.

Claim 13, line 1, change "any of claims 1-10" to ---claim 1---.

Claim 15, line 1, delete "or claim 14".

Claim 17, line 1, delete "or claim 16".

Claim 18, line 1, change "any of claims 9-11, 15 or 17" to ---claim 9---.

Claim 19, line 1, change "any of claims 11, 15, 17 or 18" to --- claim 11---.

Claim 20, line 1, change "any of the preceding claims" to ---claim 1---.

Claim 24, line 1, change "any of claims 20-23" to ---claim 20---.

Claim 25, line 1, change "any of claims 20-23" to ---claim 20---.

Claim 26, line 1, change "any of claims 20-23" to ---claim 20---.

Claim 27, line 1, change "any of claims 20-23" to ---claim 20---.

Claim 28, line 1, change "any of claims 20-23" to ---claim 20---.

Claim 35, line 1, change "any of claims 29 to 34" to ---claim 29".

Claim 36, line 1, change "any of claims 29 to 34" to ---claim 29".

Claim 37, line 1, change "any of claims 29 to 34" to ---claim 29".

Claim 38, line 1, change "any of claims 29 to 34" to ---claim 29".

Claim 39, line 1, change "any of claims 29 to 38" to ---claim 29".

Claim 40, line 1, change "any of claims 29 to 38" to ---claim 29".

Claim 41, line 1, change "any of claims 29 to 38" to ---claim 29".

Claim 42, line 1, change "any of claims 29 to 41" to ---claim 29".

Claim 43, line 1, change "any of claims 29 to 42" to ---claim 29".

Claim 44, line 1, change "any of claims 29 to 43" to ---claim 29".

Claim 45, line 1, change "any of claims 29 to 44" to ---claim 29".

Claim 51, line 1, change "any of claims 48-50" to ---claim 48".

Claim 55, line 1, change "any of claims 51 to 54" to ---claim 51".

Claim 56, line 1, change "any of claims 51 to 54" to ---claim 51".

Claim 57, line 1, change "any of claims 51 to 54" to ---claim 51".

REMARKS

Entry of the foregoing amendment to the claims upon which the International Preliminary Examination Report is based is respectfully requested prior to examination and calculation of the filing fees in the above-identified patent application.

P16370.A01

Should there be any questions, the Examiner is invited to contact the undersigned at the below listed number.

Respectfully submitted, ARONHIME et al.

Arpold Turk Reg. No. 33,094

February 13, 1998 GREENBLUM & BERNSTEIN, P.L.C. 1941 Roland Clarke Place Reston, VA 20191 (703) 716-1191

09/011634

I INTERMEDIATE TRANSFER BLANKET AND METHOD OF PRODUCING THE SAME

2

FIELD OF THE INVENTION

The present invention relates to improved intermediate transfer blankets, especially suited for transfer of liquid toner images, and methods of producing such blankets.

7 8

BACKGROUND OF THE INVENTION

9 The use of an intermediate transfer member in 10 electrostatic imaging is well known.

Various types of intermediate transfer members are known 12 and are described, for example in U.S. Patents 3,862,848, 13 4,684,238, 4,690,539 and 4,531,825, the specifications of all 14 of which are incorporated herein by reference.

Belt-type intermediate transfer members for use in l6 electrophotography are known in the art and are described, 17 inter alia, in U.S. Patents 3,893,761, 4,684,238 and 18 4,690,539, the specifications of all of which are incorporated 19 herein by reference.

The use of intermediate transfer members and members including transfer blankets, for offset ink printing, is also well known. Such blankets have characteristics which are suitable for ink transfer but they are generally not usable, per se, for liquid toner imaging.

Multi-layered intermediate transfer blankets for toner imaging are known in the art. Generally, such blankets include a thin, multi-layered, image transfer portion and a base (or body) portion which supports the image transfer portion and provides the blanket with resilience during contact with an imaging surface and/or a final substrate. While the process for producing the image transfer portion is a relatively clean process, the base portion is generally not compatible with such clean processes.

Mechanisms for continuous replacement of an imaging 35 blanket are known in the art. Such a mechanism is described, 36 for example in Japanese Publication JP 5046037, published 37 February 26, 1993, wherein a continuous sheet of transfer-38 blanket material is rolled-up in a cassette, inside a drum,

The second secon

C

20

I and a premeasured length of the blanket material is stretched circumferentially on the surface of the drum. When the stretched out length of blanket requires replacement, the used portion of the blanket is drawn into a take-up cassette, inside the drum, and a new portion of the blanket is stretched between the two cassettes. It should be noted that the length of transfer-blanket material in the cassettes is limited by the thickness of the continuous blanket and the available space within the drum.

describes patent 4,074,001 fixing roller a US 10 II electrophotography which has a 3 mm coating of a mixture of both chain ends with 12 diorganopolysiloxanes terminated at 13 diorganohydroxysilyl groups bonded to terminal silicone atoms diorganopolysiloxanes silicone), condensation type 14 (a 15 terminated at both chain ends with trialkysilyl groups (a 16 substantially unreactive silicone oil), a minor part of an 17 alkoxysilane catalyst and various amounts of fillers. thickness, the 3 mm 18 material vulcanizes, in 19 temperature.

SUMMARY OF THE INVENTION

It is an object of an aspect of the present invention to 22 provide an improved image transfer blanket for use as part of 23 an image transfer member in imaging apparatus, especially in 24 image forming apparatus using electrostatically charged toner.

It is an object of an aspect of the present invention to 26 provide an improved method and apparatus for producing a 27 multi-layered image transfer blanket.

It is an object of an aspect of the present invention to 29 provide an image transfer blanket having a base portion and an 30 image transfer portion, wherein the image transfer portion is 31 movable relative to the base portion.

It is an object of an aspect of the present invention to 33 provide a mechanism for replacing the image transfer portion 34 of the image transfer blanket without replacing the base 35 portion of the blanket.

It is a further object of some aspects of the invention 37 to provide an improved release layer for intermediate transfer 38 members and blankets.

- There is thus provided, in accordance with a preferred embodiment of the invention, a method of producing a multilayered image transfer blanket including a body portion and an image transfer portion, the image transfer portion having an image transfer surface and a back surface, comprising:
- 6 forming the image transfer portion on a carrier 7 substrate; and
- 8 transferring the image transfer portion onto the body 9 portion such that the back surface of the image transfer 10 portion faces the body portion.
- Preferably the image transfer portion is formed on the 12 carrier substrate such that the back surface of the image 13 transfer portion faces the carrier substrate.
- In a preferred embodiment of the invention transferring 15 the image transfer portion comprises:
- transferring the image transfer portion to a moving 17 carrier surface, such that at least a portion of the image 18 transfer surface is in contact with the moving surface; and
- laminating the image transfer portion onto the body 20 portion such that the back surface of the image transfer 21 portion faces the body portion.
- Preferably the method comprises curing at least one of the layers in said multi-layered blanket after transferring the image transfer portion. Preferably, the image transfer blanket comprises a polymer layer, preferably a conducting layer, interfacing the back surface of the image transfer portion and curing at least one of the layers comprises curing the polymer layer after laminating the image transfer portion onto the body portion.
- In one preferred embodiment of the invention the polymer layer is part of the body portion. Additionally or alternatively, the polymer layer is part of the image transfer portion.
- In a preferred embodiment of the invention the image 35 transfer portion comprises a release layer at the image 36 transfer surface and a conforming layer and wherein curing at 37 least one layer comprises curing the release layer and the 38 conforming layer before laminating the image transfer portion

(:

I to the body portion. In an alternative preferred embodiment of 2 the invention the release layer and the conforming layer are 3 cured after laminating the image transfer portion to the body 4 portion.

In a preferred embodiment of the invention forming the image transfer portion comprises coating the carrier substrate with a conforming layer.

8 In a preferred embodiment of the invention forming the 9 image transfer portion comprises coating the carrier substrate 10 with a barrier layer.

In a preferred embodiment of the invention forming the image transfer portion comprises coating the carrier substrate with a conductive layer.

In a preferred embodiment of the invention the conforming 15 layer comprises a plurality of layers of different hardnesses.

In a preferred embodiment of the invention forming the 17 image transfer portion comprises overcoating the conforming 18 layer with a release layer, preferably comprising a layer of 19 condensation type silicone.

There is further provided in accordance with a preferred 21 embodiment of the invention an image transfer member suitable 22 for the transfer of toner images and having an outer release 23 coating of a condensation type silicone.

24 Preferably the release layer has a thickness of less than 25 1 mm, more preferably less than 500 micrometers, even more 26 preferably less than 100 micrometers and most preferably 27 between 3 and 15 micrometers thick.

Further, the release layer preferably has less than 4% 29 filler, more preferably less than 1% filler, even more 30 preferably less than 0.1% filler.

In a preferred embodiment of the invention the outer release layer contains less than 10% silicone oil, more preferably less than 5% silicone oil, more preferably less than 1% silicone oil, most preferably little or no silicone oil.

In a preferred embodiment of the invention the outer release layer contains added crosslinker.

- I In a preferred embodiment of the invention the outer 2 release layer contains added catalyst.
- In a preferred embodiment of the invention the outer trelease layer contains added conductive material.
- In a preferred embodiment of the invention adhesion of the outer release coating to the image transfer member is nenhanced utilizing primer.
- There is further provided, in accordance with a preferred embodiment of the invention, apparatus for producing a multi-lolayered image transfer blanket including a body portion and an limage transfer portion, the image transfer portion having an
- 12 image transfer surface and a back surface, comprising:
- a carrier substrate having the image transfer portion 14 formed thereon such that the back surface of the image 15 transfer portion faces the carrier substrate and is releasable 16 therefrom; and
- a moving carrier surface, in contact with a portion of 18 the image transfer surface, which receives the image transfer 19 portion from the carrier substrate, at a first transfer 20 region, and laminates the image transfer portion onto the body 21 portion, at a second transfer region, with the back surface of 22 the image transfer portion facing the body portion.
- 23 Preferably, the apparatus further comprises a curing 24 device which cures at least one of the layers in said multi-25 layered blanket.
- There is further provided, in accordance with a preferred problement of the invention, an image transfer blanket comprising:
- 29 a transfer surface adapted to receive already formed 30 images; and
- a conforming layer substantially immediately beneath the release surface which comprises a plurality of sub-layers each having a Shore A hardness of less than 80, preferably less than 70, more preferably less than 60.
- Preferably, the sub-layers comprise at least two sub-36 layers, a relatively harder one of said sub-layers being 37 situated between is between the release surface and a 38 relatively softer one of said sub-layers. Preferably, the

- 1 relatively softer sub-layer has a Shore A hardness of less 2 than 42, less than 35, or less than 25. Preferably, the 3 relatively harder sub-layer has a Shore A hardness of greater 4 than 42, or greater than 50 .In some preferred embodiments of 5 the invention the ratio of the thickness of the relatively 6 harder sub-layer to the thickness of the relatively softer 7 sub-layer is about 1:4.
- 8 There is further provided an image transfer blanket 9 comprising:
- 10 a body portion including a layer of resilient material;
 11 and
- a multi-layered transfer portion having an image transfer surface and including a supporting base layer which is formed 14 of a substantially non-compliant material,
- wherein the supporting base layer of the transfer portion interfaces the body portion.
- 17 There is further provided in accordance with a preferred 18 embodiment of the invention a method of producing a multi-19 layered image transfer blanket comprising:
- forming a multi-layered image transfer portion having an 21 image transfer surface and a supporting base layer, the base 22 layer being formed of a substantially non-compliant material; 23 and
- 24 attaching the image transfer portion to a body portion 25 including a layer of substantially resilient material,
- wherein the supporting base layer of the transfer portion 27 interfaces the body portion.
- There is further provided, in accordance with a preferred embodiment of the invention an intermediate transfer member, which receives a toner image from an imaging surface and from this subsequently transferred, comprising:
- 32 a drum; and
- an image transfer blanket mounted on the drum, the image transfer blanket comprising:
- a body portion including a layer of resilient material; 36 and
- a multi-layered transfer portion having an image transfer surface which receives the toner image and a supporting base

Ĺ

- ! layer which is formed of a substantially non-compliant
 2 material,
- wherein the supporting base layer of the transfer portion interfaces the body portion.
- 5 Preferably, the supporting base layer comprises a layer 6 of Kapton.
- 7 There is further provided an intermediate transfer 8 member, which receives a toner image from an imaging surface 9 and from which it is subsequently transferred, comprising:
- 10 a drum;
- a resilient blanket body mounted circumferentially on the surface of the drum and having a functional length;
- a sheet of image transfer material having first and 14 second ends and having a length equal to at least twice the 15 functional length of the blanket body;
- 16 a transfer material supply member associated with the 17 first end of the sheet; and
- a transfer material take-up member associated with the second end of the sheet,
- wherein an appropriate length of the sheet is stretched 21 between the supply member and the take-up member, over the 22 functional length of the blanket body.
- 23 Preferably, a predetermined length of used-up sheet is 24 taken-up by the take-up member and replaced with approximately 25 the same length of unused sheet which is supplied the supply 26 member.
- There is further provided a carrier substrate having 28 formed thereon a multi-layered image transfer arrangement, the 29 image transfer arrangement comprising a back surface and an 30 image transfer surface, wherein the back surface of the image 31 transfer arrangement faces the carrier substrate and is 32 removably attached thereto.

1

BRIEF DESCRIPTION OF THE DRAWINGS

- The present invention will be understood and appreciated more fully from the following detailed description, taken in a conjunction with the drawings in which:
- Fig. 1 is a simplified cross-sectional illustration of an 6 image transfer member, including a multi-layered image 7 transfer blanket mounted on a drum, in accordance with a 8 preferred embodiment of the present invention;
- 9 Figs. 2A and 2B are respective top and side views of the 10 image transfer blanket of Fig. 1, in accordance with a 11 preferred embodiment of the present invention;
- Fig. 2C shows details of the multi-layered construction 13 of the image transfer blanket of Figs. 2A and 2B, in 14 accordance with one, preferred, embodiment of the present 15 invention;
- Fig. 3 is a schematic illustration of apparatus for 17 producing a multi-layered image transfer blanket, constructed 18 and operative in accordance with a preferred embodiment of the 19 present invention;
- Fig. 4 is a simplified, schematic illustration of an 21 image transfer blanket having an image transfer portion, 22 constructed in accordance with another, preferred, embodiment 23 of the present invention; and
- Fig. 5 is a simplified cross-sectional illustration of an 25 image transfer member, including the image transfer blanket of 26 Fig. 4 mounted on a drum and apparatus for renewing the image 27 transfer portion of the image transfer blanket, constructed 28 and operative in accordance with a preferred embodiment of the 29 invention.

1

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Reference is now made to Fig. 1 which is a simplified 2 3 cross-sectional illustration of an image transfer member 30, 4 including a multi-layered image transfer blanket 100 mounted 5 on a drum 102, in accordance with a preferred embodiment of 6 the present invention. Image transfer member 30 may, for some 7 embodiments of the invention, be any suitable intermediate 8 transfer member having a multilayered transfer portion such as 9 those described below or in US Patents 5,089,856 or 5,047,808 10 or in PCT Application PCT/NL 95/00188, filed June 6, 1995, the II disclosures of which are incorporated herein by reference and 12 by other structures known in the art. As is known in the art, 13 member 30 is maintained at a suitable voltage and temperature 14 for electrostatic transfer of a toner image thereto from an 15 image bearing surface, such as a photoreceptor surface. The 16 image is preferably transferred from intermediate transfer 17 member 30 onto a final substrate (not shown), such as paper, 18 preferably by heat and pressure. For the preferred toner 19 described in PCT/NL 95/00188, an image temperature of about 20 95°C at the inception of fusing is preferred.

Certain aspects of the present invention, especially the manner in which transfer blanket 100 is mounted on drum 102, are shown and described by way of example only and may vary in accordance with specific requirements and design considerations. Other preferred methods of mounting the transfer blanket on the drum are shown in the aforementioned application number PCT/NL 95/00188.

As known in the art, a plurality of single color images 29 are preferably sequentially transferred, in mutual alignment, 30 to the surface of an image transfer portion 104 of image 31 transfer blanket 100, by sequential imaging cycles. When all 32 of the desired images have been transferred to image transfer 33 blanket 100, the complete multi-color image is transferred 34 from transfer member 30 to the final substrate. Alternatively, 35 each single color image may be separately transferred to the 36 substrate via the intermediate transfer member, as known in 37 the art.

Reference is now made to Figs. 2A, 2B and 2C which schematically illustrate a preferred embodiment of image transfer blanket 100. As shown most clearly in Fig. 2C, image transfer portion 104 comprises a release layer 109 which is outermost on the blanket when it is mounted on drum 102. Underlying layer 109 is a conforming layer 111 preferably of a soft elastomer, preferably of polyurethane or acrylic and preferably having a Shore A hardness of less than about 65, more preferably, less than about 55, but preferably more than about 35. A suitable hardness value is between about 42 and about 45. Alternatively, layer 11 may have sub-layers of varying hardness, as described below.

A thin barrier layer for solvents and/or gases 114 lies 14 between layer 111 and an underlying conductive layer 115 for 15 some embodiments of the invention. In general, the order of 16 layers 114 and 115 may be reversed. Conductive layer 115 17 overlays a blanket body 116 comprising a top layer 118, a 18 compressible layer 120 and a fabric layer 122. In a preferred 19 embodiment of the invention, as described in more detail 20 below, top layer 118 is conductive and conductive layer 115 21 may be omitted.

Underlying the fabric layer there may be an adhesive 23 layer 126 which is in contact with drum 102. Alternatively, 24 layer 126 is a very soft, smooth, layer.

Drum 102 is preferably heated by an internal halogen lamp 26 heater or other heater to aid transfer of the image to the 27 release layer 109 and therefrom to the final substrate, as is 28 well known in the art. Other heating methods, or no heating at 29 all, may also be used in the practice of the invention. The 30 degree of heating will depend on the characteristics of the 31 toner and/or ink used in conjunction with the invention.

in Figs. 2A and 2B, mounting fitting 106 As shown 32 33 comprises an elongate electrically conducting bar 108, for 34 example of a metal such as aluminum, formed with a series of finger-like (in the form of 35 L-shaped mounting legs 110 36 extensions) which are also conducting, preferably of the same preferably formed integrally 108, and 37 material as bar 38 therewith. In particular, bar 108 is formed, in one preferred l embodiment, with a slot into which the end of layered part of 2 blanket 100 is inserted. Preferably, the end of the layered 3 part which is inserted into the mounting bar does not include 4 release layer 109, conforming layer 111 and barrier layer 114, 5 whereby conducting layer 115 is exposed and is therefore in 6 electrical contact with bar 108.

Alternatively, if layer 118 is conducting or layer 115 is 8 made thick enough (preferably more than 40 micrometers thick) 9 the slot can be formed with sharp internal projections which 10 pierce the outer layers of the blanket and contact conducting 11 layer 115 or conducting top layer 118.

Optionally, each of the layers beneath conducting layer 13 115 may be partially conducting (for example, by the addition of conductive carbon black or metal fibers) and the adhesive (or very soft and smooth) layer 126 may be conductive, such that current flows, additionally or alternatively, directly from the drum surface to the conducting layer. In this case layer 115 may generally be omitted.

Optionally, the conforming layer and/or the release layer are made somewhat conductive (preferably between 10^6 and 10^{12} ohm-cm, more preferably, between 10^9 and 10^{11} ohm-cm) by the addition of carbon black or between 1% and 10% of anti-static compounds such as CC-42 (Witco).

24 For the purposes of most aspects of the present 25 invention, the structure and method of attachment of the 26 blanket to drum 30 is not relevant, per se, to the invention.

In one preferred embodiment of the invention, fitting 106 28 is formed of a single sheet of metal, wherein the legs are 29 partially cut from the metal which is bent into a U-shape to 30 form the slot into which the layered portion is inserted. 31 After insertion, the outer walls of the slot are forced 32 against the layered portion to secure the layered portion in 33 the slot and, optionally, to pierce the outer surface of the 34 blanket and contact the conductive layer. The partially cut 35 out portion is bent to form the mounting legs.

In the preferred embodiment of the invention, drum 102 is 37 maintained at a potential suitable for transferring images to 38 the intermediate transfer member, for example at a negative l voltage of 500 volts, which voltage is applied, via mounting 2 fitting 106 to conductive layer 115 or 118. Thus, the source 3 of transfer voltage is very near the outer surface of transfer 4 portion 104 which allows for a lower transfer potential on the 5 drum.

Apart from differences which will be appreciated from the descriptions herein, the multi-layered blanket 100 of the present invention is generally similar to that described in PCT/NL 95/00188, except for additional preferred embodiments as described herein. However, the multi-layered blanket of the present invention is produced by a new process, as described below.

body 116 blanket appreciated that Ιt is 14 components which may contaminate at least some of the layers image transfer portion during production 15 in the 16 blanket. For example, small particles from blanket body 116, 17 which is generally formed of relatively unclean materials, may 18 break off the body portion and contaminate the relatively 19 clean layers of transfer portion 104. This may result in low 20 transfer efficiency and poor imaging quality. Therefore, in a 21 preferred embodiment of the present invention, blanket body 22 116 and image transfer portion 104 are formed separately. The 23 separately formed image transfer portion is consequently 24 laminated onto the blanket body, as described in detail below 25 with reference to Fig. 3. Conducting layer 115 may be coated 26 directly on blanket body 116 or laminated thereon together 27 with the other layers of image transfer portion 104, 28 described below. Alternatively, layer 118 is conducting and 29 layer 115 is omitted. Curing of the different layers in the 30 multi-layered blanket may be performed before, after or during 31 lamination of the two portions of the blanket.

Reference is now made also to Fig. 3 which schematically 33 illustrates apparatus 180 for forming multi-layered image 34 transfer blanket 100, constructed and operative in accordance 35 with a preferred embodiment of the invention.

In a preferred embodiment of the invention, the con-37 struction of blanket body 116 is generally similar to that 38 described in PCT/NL 95/00188. One suitable body is MCC-1129-02

I manufactured and sold by Reeves SpA, Lodi Vecchio (Milano), 2 Italy. Other preferred blanket types are described in US 3 Patents 5,047,808; 4,984,025; 5,335,054 and PCT publications 4 WO 91/03007; WO 91/14393; WO 90/14619; and WO 90/04216, which 5 are incorporated herein by reference, and in PCT/NL 95/00188. 6 Body portion 116 includes fabric layer 122, preferably formed 7 of woven NOMEX material having a thickness of about 8 micrometers, compressible layer 120, preferably comprising 9 about 400 micrometers of saturated nitrile rubber loaded with 10 carbon black to increase its thermal conductivity. Layer 120 II preferably contains small voids (about 40 - 60 % by volume) 12 and top layer 118 is preferably formed of the same material as 13 the compressible layer, but without voids. Blanket body 116 14 can be produced using production methods as are generally used 15 for the production of offset printing blankets for ink offset 16 printing.

17 Blanket body 116 is preferably sized to a relatively 18 exact thickness by abrading portions of the surface of top 19 layer 118. A preferred thickness for the finished body 116 is 20 about 700 micrometers, although other thicknesses are useful, 21 depending on the geometry of the printing system in which it 22 is used and the exact materials used in the blanket body.

The fabric side of blanket body 116 may be coated with a micrometer thick coating of silicone based adhesive (preferably, Type Q2-7566 manufactured by Dow Corning). The adhesive is covered with a sheet of mylar coated with a fluorosilicone material, such as DP 5648 Release Paper (one side coat) distributed by H.P. Smith Inc., Bedford Park, IL. This adhesive is characterized by its good bond to the surface of drum 102 and its resistance to the carrier liquid used in the liquid toner. The blanket may be removed from drum 102, when its replacement is desired, by cutting the blanket along the edge of fitting 106 and removing the blanket and fitting.

An adhesive is preferably used to assure good thermal 35 contact between the back of the blanket and the drum on which 36 it is mounted. A silicone adhesive is preferred since 37 adhesives normally used in attachment of blankets to drums in 38 the printing art deteriorate under the heat which is generated

(.

I in the underlying drum in the preferred apparatus. While the 2 temperature of the drum varies, depending on the thermal 3 resistance of the blanket and the desired surface temperature 4 of the blanket (which in turn depends on the toner used in the 5 process and the details of transfer of the toner to the final 6 substrate), the drum temperature may reach 80°C, 100°C, 120°C 7 or 150°C or more.

As an alternative to, or additional to, the adhesive 9 layer 126, a very soft conforming layer may be used at the 10 back of the blanket. A soft layer of this type will allow for 11 good thermal contact between the blanket and the heated drum 12 102 so that the temperature of the drum need not be excessive 13 in order for the outer surface of the blanket to reach its Furthermore, such а soft 14 operating temperature. 15 especially if it is very soft, will cause the blanket to 16 "cling" to the drum obviating the use of adhesive under when the blanket 17 certain circumstances. Furthermore, 18 replaced there is no adhesive residue on the drum to be 19 removed.

20 A very soft layer may be produced by the following 2! method:

- 1) 100g of Hi-Temp 4051 EP (Zeon) acrylic resin is mixed 23 with 2g NPC-50 crosslinker (Zeon) and 3g sodium stearate and 24 dissolved in toluene to give a solution of 15% non-volatile 25 solids. Optionally, up to about 40g of carbon black Pearls 130 26 (Cabot) is added.
- 27 2) A thin layer of the solution is coated onto release 28 coated mylar and dried. This process is repeated several times 29 until a thickness of preferably 20-30 micrometers is achieved.
- 3) The uncured resin is laminated to the adhesive layer 31 of a blanket produced in accordance with the invention, or 32 directly to the fabric layer. This step is preferably carried 33 out prior to the cure of the release layer.
- 34 4) The laminated structure is cured together with the 35 release layer and the release coated mylar is removed.
- The very soft conforming layer has a Shore A hardness of about 20-24 without carbon black and about 40-45 with carbon black. Softer materials are also suitable; however,

1 substantially harder materials do not adhere well to the drum 2 surface. Optionally, the trailing end of the blanket is not 3 coated with the very soft layer. The trailing edge is coated 4 with an adhesive to improve adhesion between this portion and 5 the drum or other surface to which it is attached. This is 6 especially desirable when somewhat harder materials are used 7 for the very soft layer.

8 The acrylic material may be replaced by other soft 9 elastomer materials such as soft polyurethane or nitrile 10 rubber. Other heat improving additives which have a smaller 11 effect on the hardness of the final product may be used 12 instead of carbon black, such as Fe_2O_3 or alpha aluminum 13 oxide.

Top layer 118 is preferably coated with a sub-micron layer of primer before being coated with additional layers. A leaver of primer is Dow Corning 1205 Prime Coat. The type of primer depends on the properties of the top layer and of the conductive layer. Preferably, 0.3 micron of primer is coated onto a clean top layer with a No. 0 bar in a wire-rod coating apparatus and is allowed to dry before applying the conductive layer.

Conductive layer 115 is preferably formed of an acrylic rubber loaded with conductive carbon black. The conductive layer is formed by first compounding 300 grams of Hytemp C5 4051EP (Zeon Chemicals) with 6 grams of Hytemp NPC 50 and 9 grams of sodium stearate in a two-roll mill for 20 minutes; and then dissolving 150 grams of the compounded material in 28 2000 grams of methyl ethyl ketone (MEK) by stirring for 12 hours at room temperature.

48 grams of conductive carbon black, such as, for 31 example, Printex XE2 (Degussa) are added to the solution and 32 the mixture is ground in a 01 attritor (Union Process) loaded 33 with 3/16" steel balls. Grinding proceeds at 10°C for 4 hours 34 after which time the material is diluted by the addition of 35 MEK to a concentration of 7.5-8% solids and discharged from 36 the grinder in the form of a conductive lacquer.

37 This material is coated onto layer 118 to a thickness of 38 preferably 1-3 micrometers.

In an alternate preferred embodiment of the invention, where a thicker conductive layer is desired for attachment to bar 108 by way of piercing elements, layer 118 is made conductive and layer 115 is omitted. For this embodiment a different conductive formulation is preferably used, which formulation is prepared as follows:

- 1) 100g of Hi-Temp 4051 EP (Zeon) acrylic resin and 15-25 8 grams of Printex XE-2 carbon black (Degussa) are mixed on an 9 unheated two-roll mill or Bumbury mixer for 2-4 minutes.
- 2) 2g NPC-50 crosslinker (Zeon) and 3g sodium stearate II are added to the mixture on the two roll mill and mixing is 12 continued for 4-10 minutes. The mill is kept cool to avoid 13 premature polymerization of the acrylic resin.
- 14 3) The resulting mixture is dissolved and dispersed in 15 toluene are to give a mixture containing 17% to about 30% non-16 volatile solids.
- 17 4) The resultant mixture is progressively filtered, with 18 a final filtering stage of 50 micrometers.

Layer 120 is overcoated with about 100 micrometers of the resulting material and is dried at up to 100°C for a few minutes. Several layers of this material are added until the desired thickness of 100 micrometers is reached. This layer is sized as described above. The resulting conductive layer preferably has a resistance of 15K ohms per square to 50K ohms per square.

An additional coating of primer may be added over the conductive lacquer or the conductive top layer 118 (except for the portion which is to be inserted into bar 108) before the remaining layers, i.e. the layers of image transfer portion 104, are laminated onto blanket body 116. Conductive layer 115 is preferably not cured until after lamination with portion 104, as described below.

The resistance of the conductive layer should preferably be more than about 15-20K ohms per square and preferably less than about 50K ohms per square. This value will depend on the resistivity of the layers above the conducting layer and on the aspect ratio of the blanket. In general, the resistance should be low enough so that the current flowing on the

l conducting layer (to supply leakage current through the overlying layers) does not cause a substantial variation of voltage along the surface of the blanket. The resistance of the conducting layer and, more importantly, the resistance of the overlying layers control the current flowing through the overlying layers. Generally speaking, the conductive layer has a relatively low resistance and resistivity, the conforming layer (layer 111) has a higher resistivity and the overlying release layer (layer 109) has a still higher resistivity.

shown in Fig. 3, image transfer portion 104 11 preferably formed on a carrier substrate 200 independently of 12 the formation of blanket body 116 as described above. The 13 utilized surface 202 of substrate 200 should be releasable 14 from conforming layer 111, barrier layer 114 or conducting (depending on whether barrier layer 114 15 layer 115 16 conductive layer 115 are included in image transfer portion 17 104), because portion 104 is to be subsequently removed from 18 substrate 200. Furthermore, the releasability of substrate 200 19 from portion 104 should be higher than the releasability of 20 release layer 109 from conforming layer 111, to ensure that 21 the layers in portion 104 are collectively releasable from 22 substrate 200. In a preferred embodiment of the invention, 23 substrate 200 is a sheet of metalized, preferably aluminized, 24 polyester having a thickness of between 100 micrometers and 25 175 micrometers. This material provides substrate 200 with the Ιt qualities. release and support 26 desired 27 appreciated, however, that other materials may be equally 28 suitable or more suitable for providing the desired qualities 29 of substrate 200.

preferably included in Barrier layer 114 is 31 transfer portion 104 in order to isolate the other layers in image transfer portion from body portion 116, 33 transfer portion 104 is subsequently integrated with body as described below. Such isolation may be 116, 34 portion 35 required because blanket body 116 may contain materials such 36 as anti-oxidants, anti-ozonants or other additives which may 37 migrate through the upper layers of the blanket, for example 38 as a gas when the blanket is heated during the imaging process

I and/or in the presence of carrier liquid such as Isopar L. The barrier layer should be substantially impervious to such materials in the blanket body which may migrate and/or to the carrier liquid which is used by the imaging apparatus. If this layer is omitted, under certain circumstances the additive materials can cause deterioration of the photoreceptor used by the imaging apparatus. In particular, it was found that the imaging process may become humidity dependent.

9 In a preferred embodiment of the invention, a 4-11 10 micrometer layer of polyvinyl alcohol (88% hydrolyzed) is 11 coated onto surface 202 of substrate 200.

Polyvinyl alcohol, 88% hydrolyzed, having an average molecular weight preferably between 85,000 and 145,000 (Aldrich Chemical Co. Inc., Milwaukee, WI) is dissolved in the water at 90°C by continuously stirring the mixture in a reflux system for 30 minutes. After 30 minutes, a quantity of ethanol equal to twice the quantity of water is added to the solution, the resulting polyvinyl alcohol concentration being preferably less than 10%. Higher concentration solutions can be used; however, they give a more viscous solution which is hard to spread evenly.

The solution can be deposited on surface 202 of substrate 23 200 using a fine wire rod or knife inclined at 30-45° to the 24 direction of movement of the knife or body. The solvent is 25 evaporated either by drying at room temperature or by blowing 26 hot air on the layer.

One or more coating passes are employed to give the 28 required thickness.

Too thin a layer will subsequently result in some penetration of material from body 116 into the layers of portion 104, which is correlated with reduced transfer efficiency from the photoreceptor to the intermediate transfer blanket. This reduced transfer efficiency is believed to be caused by photoreceptor deterioration. While four micrometers of material appears to be sufficient to avoid leaching, a somewhat thicker layer is preferably used.

Other barrier materials and other thicknesses may be used 38 depending on the carrier liquid used for the toner or the I gasses omitted by body 116. Other barrier materials may 2 require lesser or greater thickness depending on their 3 resistance to the carrier liquid or the gasses released by 4 body 116. Alternatively, if body 116 resists leaching by the 5 carrier liquid or does not contain materials which are 6 released (especially when body 116 is heated) or any anti-7 oxidants and/or anti-ozonants, layer 114 may be omitted.

In a preferred embodiment of the invention, barrier layer 114 on substrate 200 is overcoated with soft, conforming, 10 layer 111, formed of polyurethane or a material similar to the 11 material of the very soft layer which is optionally used for 12 layer 126, as described above. Layer 111 is formed by the 13 following process, in accordance with a preferred embodiment 14 of the invention:

One kg of pre-filtered Formez-50 polyester resin (Hagalil 16 Company, Ashdod, Israel) is dehydrated and degassed under 17 vacuum at 60°C. 600 grams of the degassed material is mixed (Aldrich) of di-butyl-tin-diluarate grams 18 with 1.4 19 degassed at room temperature for 2 hours. 30 grams of the 20 resulting material, 3.15 grams of RTV Silicone 118 (General 21 Electric) and 4.5 grams of Polyurethane cross-linker, DESMODUR 22 44V20 (Bayer) are stirred together. A 100 micrometer layer of 23 the material is coated over the preceding layer using a No. 3 24 wire rod with one or several passes, under clean conditions, 25 preferably, class 100 conditions. The coating may be cured for 26 two hours at room temperature under a clean hood to form a 27 polyurethane layer or may be cured later, together with other 28 layers.

In accordance with a second preferred embodiment of the 30 invention, layer 111 is formed by the following process:

- 1) 100g of Hi-Temp 4051 EP (Zeon) acrylic resin is mixed 32 with 2g NPC-50 crosslinker (Zeon) and 3g sodium stearate and 33 dissolved in toluene to give a solution of 15% non-volatile 34 solids. Optionally, about 44g of carbon black Pearls 130 35 (Cabot) is added.
- 36 2) A thin layer of the solution is coated onto the 37 barrier layer and dried. This process is repeated several

(:: .

I times until a thickness of preferably 100 micrometers is 2 achieved.

The layer has a Shore A hardness of about 20-24 without 4 carbon black and about 42-45 with carbon black. Softer 5 materials are also suitable; however, substantially harder 6 materials do not adhere well to the drum surface. The acrylic 7 material may be replaced by other soft elastomer materials 8 such as soft nitrile rubber, as described in detail in PCT/NL 9 95/00188, the disclosure of which is incorporated herein by 10 reference.

Layer 111 which is thus formed should have a resistance 12 of the order of about 10⁸ ohm-cm, good thermal stability at 13 the working temperature of the blanket surface, which is 14 preferably about 100°C or less.

The function of the conforming layer is to provide good 16 conformation of the blanket to the image forming surface (and 17 the image on the image forming surface) at the low pressures 18 used in transfer of the image from the image forming surface 19 to the blanket. The layer should have a Shore A hardness 20 preferably of between 25 and 65, more preferably between 40 21 and 50, more preferably between about 42 and 45. While a 22 thickness of 100 micrometers is preferred, other thicknesses, 23 between 50 micrometers and 300 micrometers can be used, with 24 75 to 125 micrometers being preferred. Too hard a layer can 25 cause incomplete transfer to the intermediate transfer member 26 of very small printed areas, such as single dots. Too soft a 27 layer can cause difficulty in removal of a paper substrate (to 28 which the image is transferred from the intermediate transfer 29 member) from the intermediate transfer member. It is often 30 difficult to achieve optimum transfer and substrate removal.

This problem is partially solved by dividing conforming layer 111 into a number of sub-layers of different hardnesses. The sub-layers may have the same thickness or different thicknesses. This embodiment is based on the discovery that paper removal appears to be most sensitive to the hardness of the upper portion of the layer and that transfer of the image to the transfer blanket is less sensitive to the hardness of this portion of the layer.

(

Such sub-layers of varying hardness and thickness may be formed in generally the same way as described above with respect to the second method of forming layer 111, with the hardness of the sub-layers being varied by changing the proportion of carbon black. The softer and harder sub-layers are laid down separately to form the total desired thickness of conforming layer 111.

It was found that varying the hardness of the harder player between 42 and 55 Shore A, the soft layer hardness between 20 and 42 and the thickness of the harder layer between 15 and 30 micrometers (the total layer thickness remaining at 100 micrometers) gave improved paper release properties. The image transfer was improved mainly for the experiments in which the hard layer was thinner and the soft layer softer. The layers are preferably formed such that the harder layer is closest to the upper portion of the layer, and the softer layer closer to the body 116 of the intermediate transfer member. It is believed that thinner hard layers and/or softer soft layers will give even better results.

In a preferred embodiment of the invention, conforming layer 111 is overcoated with release layer 109, which is formed by the following process, according to one preferred embodiment of the invention. 12 grams of RTV silicone 236 (Dow Corning) release material preferably diluted with 2 grams of Isopar L (Exxon) and 0.72 grams of Syl-off 297 (Dow Corning) are mixed together. A wire rod (bar No. 1) coating system is used, with between one and six passes, under clean conditions to achieve a preferably 3-15 micrometer, more preferably 6-12 and most preferably 8-10 micrometer release layer thickness. In practice the release layer is about 8 micrometers thick. The material is cured at room temperature for 2 hours followed by 140°C for two hours. The cured release material has a resistivity of approximately 10¹⁴ to 10¹⁵ ohm-cm (or a lesser value if a conductive material is added).

According to a second preferred embodiment of the invention, release layer 109 is formed of a condensation type silicone release layer. In general such materials are not used for thin layers, such as the approximately 3-15 micrometer,

I preferably 8 micrometer layer generally desired for the 2 present invention. However, it has been discovered that when a 3 larger than normal amount of catalyst is added and when the 4 material is preferably cured at an elevated temperature, such 5 materials do cure, even in very thin layers. While generally 6 0.1%-0.5% of catalyst is normally used, the present invention 7 uses 0.5%-2.5% catalyst preferably greater than 1%. In the 8 preferred embodiment given below, the amount of catalyst is 9 about 2.5 times the maximum normally used.

It has been found that intermediate transfer members II using such materials for release layer 109 have generally 12 longer operating lifetime and generally better printing 13 characteristics than blankets formed with release 14 according to the prior art. This is also true of blankets in 15 which the image transfer portion is formed directly onto the 16 body as in the prior art. In a preferred embodiment of the 17 invention only reactive silicone compounds are used in the 18 formation of layer 109 with as small an amount of 19 compounds as silicone oils being present, less than 20 preferably less than 5% and even more preferably less than 1% 21 of silicone oils being present. Furthermore, it has been found 22 that such materials are generally most useful when they have 23 no fillers, less than 0.1%, or only a small amount of fillers, 24 less than 4%.

Useful materials have been found to include diorganopolysiloxanes terminated at both chain ends with diorganohydroxysilyl groups bonded to terminal silicone atoms work especially well. Finally, it has been found that a mixture of such compounds gives better overall results than individual compounds.

In a preferred embodiment of the invention the release layer 109 is prepared by the following process:

a) 12 Grams of RTV 41 (general Electric) is mixed with 16 34 grams of RTV 11 (General Electric) with the fillers removed 35 (50% solids) and a 250 microliters of an 8:2 solution of 36 Stannous octoate (Sigma) in Isopar H (EXXON).

(:

- b) The mixture is coated onto the conforming layer 111 of the blanket using a wire rod and is immediately introduced into an oven at 140°C for curing for two hours.
- The filler material is preferably removed from RTV 11 by 5 dissolving 120 gm of RTV 11 in 80 grams of an Isopar H/Hexane 6 mixture (1:1). The solution is centrifuged at 7000 RPM for one 7 hour.
- 8 The resulting material has about 25% filler material, 9 comprising mostly calcium carbonate. A release layer with less 10 filler can be prepared by removing the filler material from 11 the RTV 41 as well.
- It has been found that using the individual components of 13 the mixture, namely RTV 41 and RTV 11 by themselves to form 14 release layer 109 also gives an improvement over the prior 15 art. However, the mixture appears to give a greater 16 improvement.
- According to a third preferred embodiment, a crosslinker, 18 such as ethyl silicate and conductive material, such as carbon 19 black or anti-static compounds such as CC-42 (Witco) are added 20 to the release layer 109 of the second preferred embodiment of 21 the invention. The added crosslinker provides for further 22 improvement of the mechanical properties and very thin film added while the release layer, 23 polymerization of the improved material provides for electrical 24 conductive 25 characteristics and print quality.
- Primers, such as (3-glycidoxypropyl)trimethoxysilane (ABCR, Germany) and 1205 (Dow Corning), are used to provide for maximum adhesion of the release layer 109 to the conforming layer 111.
- The release layer 109 of this embodiment is prepared as follows:
- (GE) are dissolved in 100 gm 32 a) 100 qm RTV 11 33 hexane/isopar-H (50:50 by wt.) mixture, 100 gm RTV 41 (GE) are 34 dissolved in 100 gm hexane/isopar-H mixture, and both mixtures 35 are centrifuged at 7000 RPM for 70 min. The liquid is determined, and the precipitated percent solids 36 decanted, 37 solids, comprising filler material, in this case calcium 38 carbonate, from the centrifugation is discarded.

- 1 b) An amount of RTV 11 solution which provides 60 gm RTV 2 11 solids is mixed with an amount of RTV 41 solution which 3 provides 40 gm RTV 41 solids. To this mixture is added 5 gm 4 ethyl silicate (Chordip) and 1 gm Ketjenblack 600 carbon black 5 (Akzo). The mixture is dispersed with a high shear mixer for 6 10 min.
- c) Before the conforming layer 111 of the ITM is coated with the silicone release layer 109, the conforming layer 111 must be coated with the appropriate primers to provide maximum adhesion. Using acrylic rubber as the soft layer of the conforming layer 111, it is first coated with a thin layer of (3-glycidoxypropyl)trimethoxysilane (ABCR, Germany). The primer coated blanket is heated at 50 °C for 5 min. The first primer layer is then coated with a second primer layer of 1205 (Dow Corning), and is left at room temperature for 15 min.
- d) To 10 gm of the above-described release material is added 350 microliters of a stannous octoate/isopar-H mixture 18 (4:1 by weight). A dry film thickness of about 7 microns is 19 achieved by 2-3 coatings with a wire rod. Immediately after 20 coating the transfer-portion carrying substrate 104 with the 21 release layer 109, it is placed in an oven at 140 °C for two 22 hours.
- Once the formation of image transfer portion 104 on substrate 200 is complete, the transfer-portion carrying substrate is fed to blanket-forming apparatus 180 along the direction indicated by arrow 205. An edge of transfer portion 104 is separated from surface 202 of substrate 200 and collected by a carrier drum 220, which preferably includes a drum having a smooth, preferably metal, surface 222. Surface 222 is preferably formed of very smooth, chrome-coated, stainless steel. Drum 220 preferably rotates in the direction indicated by arrow 210, at a suitable rate, such that surface 322 moves substantially at the same linear velocity as substrate 200.
- As shown in Fig. 3, release layer 109 is the upper-most 36 layer coated onto surface 202 of substrate 200 and, thus, 37 layer 109 interfaces surface 222 of drum 220. The generally 38 smooth release layer 109 will temporarily attach itself by a

1 vacuum action to the smooth, metal, surface 222 of drum 220, 2 thereby assisting in the transfer of portion 104 from 3 substrate 200 to intermediate carrier 220, at a first transfer 4 region 203.

As further shown in Fig. 3, the pre-fabricated body 6 portion 116 is fed into a second transfer region 206, between 7 intermediate carrier drum 220 and a lamination drum 212 having 8 a surface 214, along the direction indicated by arrow 215. 9 Drum 212 rotates in a sense opposite that of drum 220, as 10 indicated by arrow 217, such that there is substantially zero 11 relative motion between surfaces 222 and 214 at region 206.

At second transfer region 206, image transfer portion 104 13 attaches itself to portion 116 and is thus removed from 14 surface 222 of drum 220. Portion 104 is laminated with body 15 portion 116, resulting in the formation of the integrated, 16 multi-layered, image transfer blanket 100.

Lamination of the two portions of blanket 100 is preferably aided by heat and pressure applied by drums 220 and 19 212. In a preferred embodiment of the invention, drum 220 is 20 heated to a temperature range of between 90°C and 130°C. 21 Additionally, drum 212 may also be heated. This temperature 22 range should be suitable for aiding bonding between transfer 23 portion 104 and body portion 116, when the materials describes 24 above are used. Bonding is achieved by the uncured conductive 25 layer 115 which becomes highly adhesive in response to the 26 heat applied thereto during lamination.

As mentioned above, conductive layer 115 is preferably 28 not cured prior to lamination. However, the layers in transfer 29 portion 104, i.e. layers 109, 111 and 114, may be cured before 30 lamination, if the conductive layer is formed as part of body 31 portion 116, prior to lamination, as described above. 32 Nevertheless, if conductive layer 115 is included is formed as 33 part of image transfer portion 104, prior to lamination, all 34 the layers in portion 104 are preferably not cured before 35 lamination.

36 If layer 118 is made conductive (and layer 115 is 37 omitted) then a thin layer of the lacquer of the type used for

1 layer 115 or a glue or a primer may be used over layer 118 to 2 enhance the lamination process.

Once portions 104 and 116 are laminated, the blanket is 4 cured, for example, using a curing device 225. The cured 5 layers include the layers which were not cured prior to 6 lamination, particularly conductive layer 115 and, optionally, 7 uncured layers in image transfer portion 104. Curing device 8 225 preferably includes a heater as is well known in the art. 9 This completes the formation of multi-layered image transfer 10 blanket 100. Alternatively, strips of blanket may be cured in 11 an oven heated to between 110°C (for about one hour) and 180°C 12 (for about four minutes).

Reference is now made to Fig. 4 which schematically 14 illustrates a cross-section of an image transfer blanket 300 15 having a body portion 216 and an image transfer portion 204, 16 constructed in accordance with another, preferred, embodiment 17 of the present invention. Blanket 300 preferably includes all 18 of the layers described above with reference to Figs. 1-3, 19 i.e. layers 109, 111, 115, 118, 120, 122 and, optionally, 20 adhesive (or soft) layer 126 of blanket 100 in contrast to the integrated blanket 100, image 21 However, 22 transfer portion 204 of blanket 300 is a self-supporting layer 23 which is not necessarily laminated with body portion 216. 24 Image transfer portion 204 may be permanently or removably 25 attached to body portion 216, using a suitable adhesive, or 26 portion 204 may be used in conjunction with body portion 216 27 without being attached thereto, for example, as described in 28 detail below. To obtain these features of blanket 300, the 29 active layers of image transfer portion 204 are preferably 30 formed on a thin (including at least the range 12 micrometers, with 31 micrometers to preferably less than 32 physical stability defining the lower limit of the range) 33 intermediate base layer 250, which is formed of a relatively 34 non-compliant material such as Kapton. Base layer 250 does not 35 contaminate the other layers in transfer portion 204, during 36 formation thereof, and has sufficient strength to support the 37 other layers in portion 204. However, base layer 250 does not 38 obviate the need for body portion 216 which provides, inter 1 alia, high pressure resilience required by multi-layered 2 blanket 300. It is believed that base layer 250 does 3 not substantially affect the operation of body portion 216.

It should be noted that failure of intermediate transfer blankets is caused primarily by failure of the release properties of layer 109. Although, eventually, failure of the blanket may also be caused by failure of the resilient properties of body portion 116, the resilient properties of the body portion last much longer, at least several times longer, than the release properties of the release layer. Thus, the present invention provides a mechanism for replacing only the image transfer portion of blanket 300, as described below.

Reference is now made to Fig. 5 which schematically illustrates an image transfer member 230 using an image transfer blanket, such as blanket 300 of Fig. 4, in which transfer portion 204 is separate from body portion 216. Body portion 216 of blanket 300 is mounted on a drum 240 which protates in the direction indicated by arrow 235. Body portion 20 216 may be mounted in a manner similar to that of blanket 100 in the embodiment of Fig. 1, such that only one end of the 22 body portion is secured to a fastener member (not shown) which would be situated at the location indicated by reference 24 numeral 310.

In accordance with the present invention, image transfer 26 member 230 further includes apparatus for replacing image 27 transfer portion 204 of image transfer blanket 300 without 28 replacing body portion 216. The replacement 29 preferably includes a transfer portion supply member 260, 30 preferably a cassette containing a predetermined length of 31 new, i.e. unused, transfer portion 204, and a take up member 32 270, preferably a cassette, which collects used transfer 33 portion 204. Transfer portion 204 is preferably tightly 34 stretched over body portion 216, between an aperture 265 of 35 supply member 260 and an aperture 275 of take-up member 270. 36 To ensure that a suitable tension is maintained in transfer 37 portion 204, the transfer portion is preferably locked and/or 38 tensioned at apertures 265 and 275 using any suitable I lock/tension devices (not shown), preferably electrically 2 controlled devices. Alternatively, a take-up roller 227 and a 3 pay-out roller 278 are tensioned to assure desired tension in 4 the exposed part of portion 204.

a preferred embodiment of the invention, 6 member includes a motor-operated take-up roller 277 7 collects the used transfer portion 204. Preferably, upon 8 command from a controller (not shown), a predetermined length 9 of transfer portion 204 is collected by take-up roller 277, so 10 as to replace the transfer portion on the entire surface of II body portion 216. The controller preferably also controls 12 deactivation of the lock/tension devices at apertures 265 and before replacement of the transfer portion, and 14 reactivation of the lock/tension devices upon completion of 15 the replacement process.

It should be noted that portion 204 is much thinner than 17 body portion 216 and, thus, a longer length of transfer 18 portion may be contained in supply member 260, in comparison 19 to prior art mechanisms which replaced the entire thickness of 20 the blanket. This enables a larger number of replacements of 21 portion 204 before the entire supply of transfer portion 204 22 in member 260 is used.

Other details of preferred imaging apparatus used in 24 conjunction with the present invention are described in PCT/NL 25 95/00188, the disclosure of which is incorporated herein by 26 reference.

It should be understood that some aspects of the inven-27 28 tion are not limited to the specific type of image forming 29 system used and some aspects of the present invention are also 30 useful with any suitable imaging system which forms a liquid 31 toner image on an image forming surface and, for some aspects 32 of the invention, with powder toner systems. Some aspects of 33 the invention are also useful in systems such as those using 34 other types of intermediate transfer members such as belt or 35 continuous coated drum type transfer members. Some aspects of suitable for use with offset invention are printing specific details given above 37 systems. The (and 38 documents incorporated herein by reference) for the image

- I forming system are included as part of a best mode of carrying 2 out the invention; however, many aspects of the invention are 3 applicable to a wide range of systems as known in the art for 4 electrophotographic and offset printing and copying.
- It will be appreciated by persons skilled in the art that 6 the present invention is not limited by the description and 7 example provided hereinabove. Rather, the scope of this 8 invention is defined only by the claims which follow:

20

25





- 1. A method of producing a multi-layered image transfer member including a body portion and an image transfer portion, the image transfer portion having an image transfer surface and a back surface, comprising:
- forming the image transfer portion on a carrier substrate; and transferring the image transfer portion onto the body portion such that the back surface of the image transfer portion faces the body portion.
- 2. A method according to claim 1 wherein the image transfer portion is formed on the carrier substrate such the back surface of the image transfer portion faces the carrier substrate.
 - 3. A method according to claim 1 or claim 2 wherein transferring the image transfer portion comprises:

transferring the image transfer portion to a moving carrier surface, such that at least a portion of the image transfer surface is in contact with the moving surface, and

laminating the image transfer portion onto the body portion such that the back surface of the image transfer portion faces the body portion.

- 4. A method according to any of the preceding claims and further comprising curing at least one of the layers in said multi-layered member after transferring the image transfer portion.
 - 5. A method according to claim 4 wherein the image transfer member comprises a polymer layer interfacing the back surface of the image transfer portion and wherein curing at least one of the layers comprises curing the polymer layer after laminating the image transfer portion onto the body portion.
 - 6. A method according to claim 5 wherein the polymer layer is a conductive layer.
- 7. A method according to claim 5 or claim 6 wherein the polymer layer is part of the body portion.

November 11, 1997



15

25

- 8. A method according to claim 5 or claim 6 wherein the polymer layer is part of the image transfer portion.
- 9. A method according to any of claims 4-7 wherein the image transfer portion comprises a release layer at the image transfer surface and a conforming layer and wherein curing at least one layer comprises curing the release layer and the conforming layer before laminating the image transfer portion to the body portion.
- 10. A method according to any of claims 4-8 wherein the image transfer portion comprises a release layer at the image transfer surface and a conforming layer and wherein curing at least one layer comprises curing the release layer the conforming layer after laminating the image transfer portion to the body portion.
 - 11. A method according to any of the preceding claims wherein forming the image transfer portion comprises:


coating the carrier substrate with a conforming layer.

- 12. A method according to any of claims 1-10 wherein forming the image transfer portion comprises:
- 20 coating the carrier substrate with a barrier layer.
 - 13. A method according to any of claims 1-10 wherein forming the image transfer portion comprises:

coating the carrier substrate with a conductive layer.

- 14. A method according to claim 13 wherein forming the image transfer portion comprises: coating the conductive layer with a barrier layer.
- 15. A method according to claim 12 or claim 14 wherein forming the image transfer portion comprises:

coating the barrier layer with a conforming layer.



10

20

- 16. A method according to claim 14 wherein forming the image transfer portion comprises:

 coating the barrier layer with a conductive layer.
- 17. A method according to claim 13 or claim 16 wherein forming the image transfer portion comprises:

coating the conductive layer with a conforming layer.

- 18. A method according to any of claims 9-11, 15 or 17 wherein the conforming layer comprises a plurality of layers of different hardnesses.
- 19. A method according to any of claims 11, 15, 17, or 18 wherein forming the image transfer portion comprises:

overcoating the conforming layer with a release layer.

- 20. A method according to any of the preceding claims wherein the release layer comprises a layer of condensation type silicone.
 - 21. A method according to claim 20 wherein the condensation type silicone contains less than 4% filler material.
 - 22. A method according to claim 20 wherein the condensation type silicone contains less than 1% filler material.
- 23. A method according to claim 20 wherein the condensation type silicone contains less than 0.1% filler material.
 - 24. A method according to any of claims 20-23 wherein the release layer has a thickness of less than 1 mm.
- 25. A method according to any of claims 20-23 wherein the release layer is less than 200 micrometers thick.

30

- 26. A method according to any of claims 20-23 wherein the release layer is Tess than 100 micrometers thick.
- 27. A method according to any of claims 20-23 wherein the layer is less than 50 micrometers thick.
 - 28. A method according to any of claims 20-23 wherein the layer is between about 3 and about 15 micrometers thick.
- 29. An image transfer member suitable for the transfer of toner images and having an outer release layer of a condensation type silicone.
 - 30. An image transfer member according to claim 29 wherein the layer has a thickness of less than 1 mm.
 - 31. An image transfer member according to claim 29 wherein the layer is less than 200 micrometers thick.
- 32. An image transfer member according to claim 29 wherein the layer is less than 100 micrometers thick.
 - 33. An image transfer member according to claim 29 wherein the layer is less than 50 micrometers thick.
- 25 34. An image transfer member according to claim 29 wherein the layer is between about 3 and about 15 micrometers thick.
 - 35. An image transfer member according to any of claims 29 to 34 wherein the outer release layer contains less than 10% silicone oil.
 - 36. An image transfer member according to any of claims 29 to 34 wherein the outer release layer contains less than 5% silicone oil.



25



- 37. An image transfer member according to any of claims 29 to 34 wherein the outer release layer contains less than 1% silicone oil.
- 38. An image transfer member according to any of claims 29 to 34 wherein the outer release layer contains essentially no silicone oil.
 - 39. A method according to any of claims 29 to 38 wherein the condensation type silicone contains less than 4% filler material.
- 40. A method according to any of claims 29 to 38 wherein the condensation type silicone contains less than 1% filler material.
- 41. A method according to any of claims 29 to 38 wherein the condensation type silicone contains less than 0.1% filler material.
 - 42. An image transfer member according to any of claims 29 to 41 wherein the outer release layer contains added crosslinker.
- 43. An image transfer member according to any of claims 29 to 42 wherein the outer release layer contains added catalyst.
 - 44. An image transfer member according to any of claims 29 to 43 wherein the outer release layer contains added conductive material.
 - 45. An image transfer member according to any of claims 29 to 44 wherein adhesion of the outer release layer to the image transfer member is enhanced utilizing primer.
- 46. Apparatus for producing a multi-layered image transfer member including a body portion and an image transfer portion, the image transfer portion having an image transfer surface and a back surfaced, comprising:



15

25

a carrier substrate having the image transfer portion formed thereon such that the back surface of the image transfer portion faces the carrier substrate and is releasable therefrom; and

a moving carrier surface, in contact with a portion of the image transfer surface, which receives the image transfer portion from the carrier substrate, at a first transfer region, and laminates the image transfer portion onto the body portion, at a second transfer region, with the back surface of the image transfer portion facing the body portion.

- 47. Apparatus according to claim 46 and further comprising a curing device which cures at least one of the layers in said multi-layered member.
- 48. An image transfer member comprising:
 - a transfer surface adapted to receive already formed images; and
- a conforming layer substantially immediately beneath the release surface which comprises a plurality of sub-layers each having a Shore A hardness of less than 80.
- 49. An image transfer member according to claim 48 wherein the sub-layers each have a shore A hardness of less than 70.
- 50. An image transfer member according to claim 48 wherein the sub-layers each have a shore A hardness of less than 60.
 - 51. An image transfer member according to any of claims 48-50 wherein the sub-layers comprise at least two sub-layers, a relatively harder one of said sub-layers being situated between the release surface and a relatively softer one of said sub-layers.
 - 52. An image transfer member according to claim 51 wherein the relatively softer sub-layer has a Shore A hardness of less than 42.
- 53. An image transfer member according to claim 51 wherein the relatively softer sub-layer has a Shore A hardness of less than 35.



15

25

- 54. An image transfer member according to claim 51 wherein the relatively softer sub-layer has a Shore A hardness of less than 25.
- 55. An image transfer member according to any of claims 51 to 54 wherein the relatively harder sub-layer has a Shore A hardness of greater than 42.
 - 56. An image transfer member according to any of claims 51 to 54 wherein the relatively harder sub-layer has a Shore A hardness of greater than 50.
- 57. An image transfer member according to any of claims 51 to 54 wherein the ratio of thickness of the relatively hard sub-layer to the thickness of the relatively softer sub-layer is about 1:4.
 - 58. An image transfer blanket comprising:
 - a body portion including a layer of resilient material; and
 - a multi-layered transfer portion having an image transfer surface and including a supporting base layer which is formed of a substantially non-compliant material,

wherein the supporting base layer of the transfer portion interfaces the body portion.

- 59. An image transfer blanket according to claim 58 wherein the supporting base layer comprises a layer of Kapton.
 - 60. A method of producing a multi-layered image transfer blanket comprising:

forming a multi-layered image transfer portion having an image transfer surface and a supporting base layer, the base layer being formed of a substantially non-compliant material; and

attaching the image transfer portion to a body portion including a layer of substantially resilient material,

wherein the supporting base layer of the transfer portion interfaces the body portion.

- 30 61. An intermediate transfer member, which receives a toner image from an imaging surface and from which it is subsequently transferred, comprising:
 - a drum; and

20

25



5

an image transfer blanket mounted on the drum, the image transfer blanket comprisings

a body portion including a layer of resilient material; and

a multi-layered transfer portion having an image transfer surface which receives the toner image and a supporting base layer which is formed of a substantially non-compliant material.

wherein the supporting base layer of the transfer portion interfaces the body portion.

- 62. An intermediate transfer member according to claim 60 wherein the supporting base layer comprises a layer of Kapton.
- 10 63. An intermediate transfer member, which receives a toner image from an imaging surface and from which it is subsequently transferred, comprising:
 - a drum;
 - a resilient blanket body mounted circumferentially on the surface of the drum and having a functional length;
 - a sheet of image transfer material having first and second ends and having a length equal to at least twice the functional length of the blanket body;
 - a transfer material supply member associated with the first end of the sheet; and
 - a transfer material take-up member associated with the second end of the sheet,
 - wherein an appropriate length of the sheet is stretched between the supply member and the take-up member, over the functional length of the blanket body.
 - 64. An intermediate transfer member according to claim 63 wherein a predetermined length of used-up sheet is taken-up by the take-up member and replaced with approximately the same length of unused sheet which is supplied the supply member.
 - 65. A carrier sheet having formed thereon a multi-layered image transfer arrangement, the image transfer arrangement comprising a back surface and an image transfer surface, wherein the back surface of the image transfer arrangement faces the carrier sheet and is removably attached thereto.

I

ABSTRACT OF THE INVENTION

A multi-layered image transfer blanket and a method of producing same, including a body portion and an image transfer portion, the image transfer portion having an image transfer surface and a back surface, comprising forming the image transfer portion on a carrier substrate and transferring the image transfer portion onto the body portion such that the back surface of the image transfer portion faces the body portion. Preferably, the image transfer portion is formed on the carrier substrate such that the back surface of the image transfer portion faces the image transfer portion is formed on the carrier substrate such that the back surface of the image transfer portion faces the carrier substrate.

1/4







FIG. 1


{· ·








3/4




A set of the first of the control of

4/4

FIG. 4





COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY (Includes Reference to PCT International Applications)

Attorney's Docket Number

P16370

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

INTERMEDIATE TRANSFER BLANKET AND METHOD OF PRODUCING THE SAME

the specification of which (check only one item below):

ļ≟ ļ∏

is attached hereto.
was filed as United States applications
Serial No. <u>09/011.634</u>
on 13 February 1998
and was amonded
on 13 February 1998 (if applicable).
was filed as PCT international application
Number
on
and was amended under PCT Article 19
on(if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

PRIOR FOREIGN/PCT APPLICATION(S) AND ANY PRIORITY CLAIMS UNDER 35 U.S.C. 119:

COUNTRY (if PCT, indicate "PCT")	APPLICATION NUMBER	DATE OF FILING (day, month, year)	PRIORITY CLAIMED UNDER 35 USC 119
ISRAEL	114,992	17 August 1995	■YES □NO
			□ YES □ NO
			☐ YES ☐ NO
			□ YES □ NO
			dyes dno

Combined Declaration For Patent Application and Power of Attorney (Continued) (Includes Reference to PCT International Applications)

ATTORNEY'S DOCKET NUMBER

I hereby claim the benefit under Title 35, United States Code §120 of any United States application(s) or PCT international application(s) designation the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in that/those prior application(s) in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing date of the prior application(s) and the national or PCT international filing date of this application.

PRIOR U.S. APPLICATIONS OR PCT INTERNATIONAL APPLICATIONS DESIGNATING THE U.S. FOR BENEFIT UNDER 35 U.S.C. 120;

	u.s.	APPLICATIO	NS	ST	ATUS (Check O	ne/
U.S. APPLICATION	NUMBER		U.S. FILING DATE	PATENT	PENDING	ABANDONED
PCT A	APPLICATION	NS DESIGNA	TING THE U.S.			
PCT APPLICATION NO.	PCT FILT	ING DATE	J.S. SERIAL NUMBER ASSIGNED (IF ANY)	,		

The undersigned hereby authorizes the U.S. attorney or agent named herein to accept and follow instructions from either his foreign patent agent or corporate representative, if any, as to any action to be taken in the Patent and Trademark Office regarding this application without direct communication between the U.S. attorney or agent and the undersigned. In the event of a change in the persons from whom instructions may be taken, the U.S. attorney or agent named harein will be so notified by the undersigned.

POWER OF ATTORNEY: As a named inventor, I hereby appoint the attorney(s) and/or agents(s) associated with the Customer Number provided below to prosecute this application and transact all business in the Patent and Trademark Office connected therewith, and direct that all correspondence be addressed to that Outcomer Number:

CUSTOMER NUMBER 7056

The appointed attorneys presently include:

Neil F. Greenblum, Reg. No. 28,394 Bruce H. Bernetein, Reg. No. 29,027 Roger P. Glass, Reg. No. 30,841 James L. Rowland, Reg. No. 32,674 Arnold Turk, Reg. No. 33,094

> At: Greenblum & Bernstein, P.L.C. 1941 Roland Clarke Piace

Reston, VA 20191

nnec	t i aletnione calle to	Greenblum & Bernstein, P.L.C. (703)	10-3101	
	FULL NAME OF INVENTOR	FAMILY NAME ARONHIME ARONHIME	FIRST GIVEN NAME Marc	SECOND GIVEN NAME
2 0 1	RESIDENCE &	CITY	STATE OR FOREIGN COUNTRY ISRAEL	COUNTRY OF CITIZENSHIP ISRAEL
a Car	POST OFFICE ADDRESS	POST OFFICE ADDRESS Lutzki 9/7	CITY Rehovot	STATE & ZIP CODE/COUNTRY 76251 ISRAEL
2	FULL NAME OF INVENTOR	FAMILY NAME AVADIC 2-\$\Phi\$	first given name Frida	SECOND GIVEN NAME
2	residence & Citizenship	CITY Rishon L'Tzion TLX	STATE OR FOREIGN COUNTRY ISRAEL	COUNTRY OF CITIZENSHIP ISRAEL
	POST OFFICE ADDRESS	POST OFFICE ADDRESS Berenstein 27/24	CITY Rishon L'Tzion	STATE & ZIP CODE/COUNTRY 75503 ISRAEL
2	FULL NAME OF INVENTOR	FAMILY NAME IDAN 3-06	PIRST GIVEN NAME David	SECOND GIVEN NAME
3	RESIDENCE & CITIZENSHIP	CITY Ashdod TLX	STATE OR FOREIGN COUNTRY ISRAEL	COUNTRY OF CITIZENSHIP ISRAEL
	POST OFFICE ADDRESS	POST OFFICE ADDRESS Harci Shomron 3/10	CITY Ashdod	STATE & ZIP CODE/COUNTRY 17719 ISRAEL

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that wilfful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such wilfful false statements may jeopardize the validity of the application or any patent issuing thereon.

01 1100 14 01 010 CHING CH240 40		
SIGNATURE OF INVENTOR 201	SIGNATURE OF INVENTOR 202	SIGNATURE OF INVENTOR 203
Mari . alcoline	AP	Thavid
DATE	DATE	DATE
1/2/48	8/3/98	8/3/94

Full name of Fourth Inventor KLEIN, Nava	
erth Inventor's signature	. 4/3/95
Residence Rishon L'Tzion, ISRAEL TLX	Date
Citizenship ISRAEL	
Post Office Address Meirovitch 37, Rishon L'Tzion, 75319 ISRAEL	
Full name of Fifth Inventor KOWAL, Yael	
· • · · · · · · · · · · · · · · · · · ·	11/60
th Inventor's signature Yav Koral	
Residence Tel Aviv, ISRAEL TLX	
Citizenship ISRAEL	
Post Office Address Wormaiza 6, Tel Aviv, 62642 ISRAEL	
Post Office Address	
Full name of Sixth Inventor LANDA. Benny	
X ~ /	8/3/9
xth Inventor's signature	Date
Residence Nes Ziona, ISRAFI TLX	
Citizenship CANADA	
Post Office Address 26 Itamar Ben Avi Street, Kfar Aharon Nes Ziona	a, 74051 ISRAEL
7-90	
Full name of Seventh Inventor LAVON. Amiran	1 // 1/25
renth Inventor's signature	
Residence Bat Yam, ISRAEL TLX	
Citizenship ISRAEL	
Post Office Address Balfour 143, Bat Yam, 59576 ISRAEL	

- **- 1**

Full name of Eighth Inventor NIV, Yehuda	
	8/3/9
ghth Inventor's signature	Date
Residence Nes Tziona, ISRAEL TLX	
Citizenship ISRAEL	
Post Office Address Kfar Aharon 11, Nes Tziona, 74051 ISRAEL	
9.00	
Full name of Ninth Inventor TEPER, Carlos	
Full name of which Inventor	8/3/98
Ninth Inventor's signature	Date
Residence Rehovot, ISRAEL ILX	
Healdering	
Citizenship ISRAEL Post Office Address Herzl 190, Rehovot, 76268 ISRAEL	
Ollizoriorii ————————————————————————————————	
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor	<u>8/3/</u> Date
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature	8/3/
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence	8/3/
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence	8/3/
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship	8/3/
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship Post Office Address	8/3/
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship Post Office Address	8/3/
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship Post Office Address	8/3/
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship Post Office Address Full name of Eleventh Inventor	<u>8/3/</u> Date
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship Post Office Address Full name of Eleventh Inventor	<u>8/3/</u> Date
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship Post Office Address Full name of Eleventh Inventor Leventh Inventor's signature	
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Post Office Address Full name of Eleventh Inventor Leventh Inventor's signature Residence Residence Residence	<u>8/3/</u> Date
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Citizenship Post Office Address Full name of Eleventh Inventor Leventh Inventor's signature	<u>8/3/</u> Date
Post Office Address Herzl 190, Rehovot, 76268 ISRAEL Full name of Tenth Inventor Tenth Inventor's signature Residence Post Office Address Full name of Eleventh Inventor Leventh Inventor's signature Residence Residence Residence	<u>8/3/</u> Date